




LIR17500-12 • Li-ion cylindrical rechargeable battery

1. Scope

This specification describes the basic performance, technical requirement, testing method, warning and caution of the Li- ion cylindrical rechargeable battery .

2. Products assembly drawing and size



3. Specification

NO.	Item	Parameter
3.1	Typical Capacity	1230mAh @ 0.2C Discharge
	Minimum capacity	1200mAh @ 0.2C Discharge
3.2	Nominal Voltage	3.7V
3.3	Standard Charge	CC/CV, 0.2C ₅ A, 4.20V
3.4	Standard Discharge	CC, 0.2C ₅ A, 3.00V
3.5	End-of-charge Voltage	4.20V±0.05V
3.6	End-of-charge Current	0.02C ₅ A (At CV mode)
3.7	End-of-discharge Voltage	3.00 V
3.8	Charging Time	8.0 hours (standard charge)
3.9	Quick Charge Current	1200mA (1.0C ₅ rate)
3.10	Quick Discharge Current	2400mA (2.0C ₅ rate)
3.11	Maximum instantaneous pulse discharge current	3600mA (3.0C ₅ rate)
3.12	Initial Impedance	Max:55mΩ
3.13	Weight	Approx: 27.5±2g
3.14	Operating temperature	Charging: 0°C~45°C Discharging: -20°C~60°C
3.15	Storage temperature	-5°C~35°C
3.16	Storage Humidity	≤75% RH
3.17	Appearance	Without scratch, distortion, contamination and leakage
3.18	Standard environmental condition	Temperature: 25±2°C Humidity: 45-75%RH Atmospheric Pressure: 86-106 KPA
3.19	Temperature dependence of discharge capacity: @ 0.2C discharge	

Charge temperature	Discharge temperature				
25°C	-10°C	0°C	15°C	25°C	40°C
Relative Capacity	50%	80%	90%	100%	100%

4. General performance

NO.	Item	Test Methods and Condition	Criteria
4.1	0.2C Capacity	After standard charging, rest battery for 10min, then discharging at 0.2C to voltage 3.0V, recording the discharging time.	≥300min
4.2	Cycle Life	Constant current 0.5C charge to 4.2V, then constant voltage charge to current declines to 0.01C, rest 10min, constant current 0.5C discharge to 3.0V, rest 10min. Repeat above steps till continuously discharging capacity higher than 80% of the initial capacities of the cells.	≥300 times
4.3	Capability of keeping electricity	20±5°C, After standard charging, rest the battery 28days, discharging at 0.2C to voltage 3.0V, recording the discharging time.	≥240min

5. Environment performance

NO.	Item	Test Methods and Condition	Criteria
5.1	Discharge at high temperature	After standard charging, rest the cells 4h at 60±2°C, then discharging at 1C to voltage 3.0V, recording the discharging time.	≥54min
5.2	Discharge at low temperature	After standard charging, rest the cells for 16h at -20±2°C, then discharging at 0.2C to voltage 3.0V, recording the discharging time.	≥210min
5.3	Thermal shock	Put the cells in the oven. The temperature of the oven is to be raised at 5±2°C per minute to a temperature of 130±2°C and remains 30 minutes.	No fire or explosion

6. Safe characteristic

NO.	Item	Test Methods and Condition	Criteria
6.1	Over charge testing	At 20±5°C, charging cells with constant current 2C to voltage 5.0V, Stop test till cells temperature 10°C lower than max temperature.	No fire or explosion
6.2	Over discharge testing	At 20±5°C, According to the requirements of standard charge, the cells will be discharge to cut-off voltage, then The discharged cell is then subjected to a forced discharge at constant current 1C to -4.2V. The total duration for the forced discharge testing is 90 min.	No fire or explosion
6.3	Short-circuit testing	At 55±5°C, After standard charging, connect cells anode and cathode by wire which impedance less than 80±20mΩ, The cell remains on test for 24 h or until the surface temperature declines by 20% of the maximum temperature rise, whichever is the sooner.	No fire or explosion

Note: Above testing of safe characteristic must be with protective equipment.

7. Cautions in use

To ensure proper use of the battery please read the manual carefully before using it. Handling.

- Do not expose to, dispose of the battery in fire.
- Do not put the battery in a charger or equipment with wrong terminals connected.
- Avoid shorting the battery
- Avoid excessive physical shock or vibration.
- Do not disassemble or deform the battery.
- Do not immerse in water.
- Do not use the battery mixed with other different make, type, or model batteries.
- Keep out of the reach of children.
- Battery must be charged in appropriate charger only.
- Never use a modified or damaged charger.
- Do not leave battery in charger over 24 hours.
- Store the battery in a cool, dry and well-ventilated area.
- Regulations vary for different countries. Dispose of in accordance with local regulations.

8. Battery operation instruction

8.1 Charging

Charging current: Cannot surpass the biggest charging current which in this specification book stipulated.

Charging voltage: Does not have to surpass the highest amount which in this specification book stipulated to decide the voltage.

Charge temperature: The battery must carry on the charge in the ambient temperature scope which this specification book stipulated.

Uses the constant electric current and the constant voltage way charge, the prohibition reverse charges. If the battery positive electrode and the cathode meet instead, can damage the battery.

8.2 Discharging current

The discharging current does not have to surpass this specification book stipulation the biggest discharging current, the oversized electric current electric discharge can cause the battery capacity play to reduce and to cause the battery heat.

8.3 Discharge temperature

The battery discharge must carry on in the ambient temperature scope which this specification book stipulated.

8.4 Over-discharges

After the short time excessively discharges charges immediately cannot affect the use, but the long time excessively discharges can cause the battery the performance, battery function losing. The battery long-term has not used, has the possibility to be able to be at because of its automatic flashover characteristic certain excessively discharges the condition, for prevented excessively discharges the occurrence, the battery should maintain the certain electric quantity.

8.5 Storing the batteries

The battery should store in the product specification book stipulation temperature range. If has surpasses above for six months the long time storage, suggested you should carry on additional charge to the battery.

9. Warranty

The warranty is specified in our warranties section of *Terms of Sales*. If the product is to be stored for more than three months it is necessary to perform the appropriate maintenance to ensure the good condition of the batteries. Consult our annex to the *Terms of Sales* on the recommended maintenance.

10. Other the chemical reaction

Because batteries utilize a chemical reaction, battery performance will deteriorate over time even if stored for a long period of time without being used. In addition, if the various usage conditions such as charge, discharge, ambient temperature, etc. are not maintained within the specified ranges the life expectancy of the battery may be shortened or the device in which the battery is used may be damaged by electrolyte leakage. If the batteries cannot maintain a charge for long periods of time, even when they are charged correctly, this may indicate it is time to change the battery.

11. Note

Any other items which are not covered in this specification shall be agreed by both parties.